



630 J Street Eureka, California 95501 (707) 444-3024

## Standard Specifications for Redwood Lumber

### Redwood Dressed Sizes

Thicknesses apply to all widths, and widths to all thicknesses. Sizes are given in inches and millimeters. Metric units are based on actual size.

#### CERTIFIED KILN DRIED OR S-DRY LUMBER

Standard Thicknesses <sup>1</sup>			Standard Widths		
Nominal (in.)	Dressed (in.)	Dressed (mm)	Nominal (in.)	Dressed (in.)	Dressed (mm)
3/8	5/16	8	2	1-1/2	38
1/2	7/16	11	3	2-1/2	64
5/8	9/16	14	4	3-1/2	89
3/4	5/8	16	5	4-1/2	114
1	3/4	19	6	5-1/2	140
1-1/4	1	25	8	7-1/4	184
1-1/2	1-1/4	32	10	9-1/4	235
2	1-1/2	38	12	11-1/4	286

#### GREEN LUMBER 3/4" TO 4" THICK

Standard Thicknesses <sup>1</sup>			Standard Widths		
Nominal (in.)	Dressed (in.)	Dressed (mm)	Nominal (in.)	Dressed (in.)	Dressed (mm)
3/4	11/16	17	2	1-9/16	40
1	25/32	20	3	2-9/16	65
1-1/4	1-1/32	26	4	3-9/16	90
1-1/2	1-9/32	33	5	4-9/16	116
2	1-9/16	40	6	5-9/16	141
2-1/2	2-1/16	52	8	7-3/8	187
3	2-9/16	65	10	9-3/8	238
4	3-9/16	90	12	11-3/8	289

#### GREEN TIMBERS

Standard Thicknesses <sup>1</sup>			Standard Widths		
Nominal (in.)	Dressed (in.)	Dressed (mm)	Nominal (in.)	Dressed (in.)	Dressed (mm)
5	4-1/2	114	5	4-1/2	114
6	5-1/2	140	6	5-1/2	140
8	7-1/2	190	8	7-1/2	190
10	9-1/2	241	10	9-1/2	241
12	11-1/2	292	12	11-1/2	292
Over 12	Off 1/2	Off 13	Over 12	Off 1/2	Off 13

<sup>1</sup> Boards less than the minimum thickness for nominal 1-inch but 5/8 inch (16 mm) or greater thickness dry (11/16 inch [17 mm] green) shall be regarded as ALS lumber, but such boards shall be marked to show the size and condition of seasoning at the time of dressing. They shall also be distinguished from nominal 1-inch boards on invoices and certificates.